

CSI SPECIFICATIONS

Waterproofing and Maintenance of Concrete

Leak Repair, Concrete Repair, Crystalline Waterproofing
Division 3, Division 7



Note to Specifier: This guide specification includes materials and installation procedures to repair, waterproof and protect concrete with crystalline technology. Successful installation of these systems will restore water tightness, greatly reduce concrete deterioration, prolong service life and reduce future maintenance expenses. The procedures are suitable for the repair of common concrete deficiencies such as leaking or non-leaking cracks, spalls, honeycombs, and restoration and maintenance of concrete cover. The completed system provides protection from the effects of water, chlorides, corrosion, ASR and aggressive chemicals. The guide specification should be adapted to suit the needs and conditions of the project. The content may be included in Division 3 (03 01 00 Maintenance of Concrete) or Division 7 (07 16 16 - crystalline waterproofing) as applicable.

Part 1 General

1.1 Summary

- A. This specification is intended to be read as a whole by all parties involved in the project. The general contractor is responsible to make clear to any subcontractors the scope of their work and coordinate work between different trades.

1.2 System Description

- A. This specification describes the patching, repair, surface restoration and protection of exterior horizontal and vertical surfaces of portland cement concrete.
- B. The system consists of the following products:
 1. Krystol T1 - Penetrating Crystalline Surface Treatment - Resurfaces and waterproofs concrete. Used to ensure low permeability and to seals cracks and microcracks. Provides uniform surface and texture to weathered concrete.
 2. Krystol Plug - Used to stop active leaks to allow permanent repairs to be completed.
 3. Krystol Repair Grout – Used to make permanent, durable and waterproof repairs to concrete (i.e. cracks and honeycombs). Used as a parge coat to resurface damaged concrete cover or rough, irregular surfaces.

1.3 Related Sections

- A. Section 07 16 16 Crystalline Waterproofing
- B. Section 03 61 00 Cementitious Grouting

1.4 References

- A. The following standards are applicable to this section:
 1. ASTC 39 – Compressive strength
 2. ASTM C1583 - Bond Strength by direct tension (Pull-off Method).
 3. DIN 1048-5 – Water Permeability
 4. USACE CRD C48 – Water Permeability
 5. CAN/NSF/ANSI No. 61 – Drinking Water System Components

CSI SPECIFICATIONS

03 01 30 CONCRETE MAINTENANCE

1.5 Quality Assurance

- A. Manufacturing Qualifications: The manufacturer of the specified products shall follow a Factory Production Control system certified by agencies accredited to ISO 7065 - Conformity assessment - Requirements for bodies certifying products, processes and services.
- B. Contractor Qualifications: The contractor must be qualified in the field of concrete repair with a successful track record of at least 5 years. The contractor will maintain qualified personal trained by a manufacturer's technical representative.
- C. Store and apply materials in accordance with the product label and product SDS, or as required by local, state or federal authorities.

1.6 Delivery, Storage and Handling

- A. All materials must be delivered in original, unopened containers with the manufacturer's name, label, and batch numbers. Remove damaged material from the site immediately.
- B. Store all materials off the ground and protect from rain, freezing or excessive temperature ready to use.

1.7 Job Conditions

- A. Do not apply below 4°C (40 °F), or if it is raining or snowing, or if such weather conditions are imminent.

1.8 Submittals

- A. Submit copies of the manufacturer's literature, to include: Technical Data Sheet (TDS), Safety Data Sheet (SDS), Application Instructions (AI).
- B. Qualification Statements
 1. Written notice from installer confirming experience in similar repair work.
 2. Submit letter of contractor training by manufacturer.

1.9 Warranty

- A. Manufacturer's warranty: Provide written manufacturer's warranty against defects in materials and manufacturing for a period of 10 Years - Concrete Repair Products, beginning with the date of substantial completion of the work.

Part 2 Products

2.1 Manufacturer

- A. Basis of Design
Kryton International Inc.
Toll Free: 1.800.268.8280
E-mail: info@kryton.com
Website: www.kryton.com
- B. The following products manufactured by Kryton International Inc. conform to the requirements.
 1. Krystol T1 (Product Code K-210)
 2. Krystol Repair Grout (Product Code K-510)
 3. Krystol Plug (Product Code K-620)
- C. Substitutions: Not permitted.

CSI SPECIFICATIONS

03 01 30 CONCRETE MAINTENANCE

2.2 General Requirements:

- A. The concrete repair products shall be a blend of portland cement, specially graded, non-reactive aggregates, and additives designed to meet the requirements of this specification.
- B. All materials shall be non-combustible, both before and after installation.
- C. All materials must be supplied as a sealed, factory blended unit.

2.3 Performance Criteria

Note to Specifier: Krystol T1 is available in Grey or White.

- A. Crystalline Waterproofing and Protective Coating
 - 1. Appearance <Grey> <White>
 - 2. VOC content – Zero (0 g/L)
 - 3. Working Time – 30 min (20°C / 68°F, 50% RH)
 - 4. Hardening Time – 5 hours (20°C / 68°F, 50% RH)
 - 5. Hydrostatic head resistance – 140 m (460 feet)
 - 6. Crack Sealing – up to 0.5mm (0.02 inches)
 - 7. Pull off strength – (ASTM D4541) – 3.1 MPa (450 psi)
 - 8. Water Permeability – DIN 1048-5 – reduced 75-85%
 - 9. Water Permeability – USACE CRD C48 – reduced 90%
 - 10. Integral Protection:
 - 1. Crystal growth verified microscopically 100 mm (4 inches) away from the coated surface.
 - 2. Water penetration - DIN 1048-5 – reduced 51% when tested after removal of the crystalline surface coating.
 - 11. Sulfate Resistance – No loss of strength after 21 cycles in high sulfate solution.
 - 12. Chloride Ion Penetration – reduced 94.6% at a depth of 15 mm (0.5 inches) after 90-day ponding with 10% calcium chloride.
 - 13. Water Absorption – BS 1881: Part 2 – Negligible – “Too impermeable to be sensitive to a longer-term test.”
 - 14. Shape of Crystal - Manufacturer must present independent evidence of waterproofing crystals using both optical imaging and scanning electronic microscope (SEM) to verify waterproofing crystals are needle shaped.
 - 15. Potable Water – Certified to CAN/NSF/ANSI No 61.
- B. Fiber-Reinforced Crystalline Concrete Repair Grout
 - 1. Color - Concrete Grey
 - 2. Working time (20°C / 68°F, 50% RH) - 30 minutes
 - 3. Hardening time (20°C / 68°F, 50% RH) - 1 to 1.5 hours.
 - 4. Hydrostatic head resistance - USACE CRD-C48, 140 m (460 feet)
 - 5. Compressive Strength (ASTM C109)
 - 1. 16 MPa (2300 psi) @ 1 day
 - 2. 38 MPa (5500psi) @ 3 days
 - 3. 45 MPa (6500 psi) @ 7 days
 - 4. 49 MPa (7100psi) @ 28 days
 - 5. 52 MPa (7500psi) @ 56 days
 - 6. Pull-off Strength (ASTM C1583) - 2.8 MPa (400 psi)

CSI SPECIFICATIONS

03 01 30 CONCRETE MAINTENANCE

C. Plug Compound

1. Appearance – dark grey powder
2. Working Time – 1 minutes (20°C/ 68°F, 50% RH)
3. Hardening Time – 2 minutes (20°C/ 68°F, 50% RH)
4. Compressive strength (ASTM C109)
 1. > 40 MPa (5800 psi) at 7 days.

Part 3 Execution

Note to Specifier: Detailed installation information is given in Kryton Application Instructions # 5.12 (Leak Repair), 5.22 (general repairs and parge coat) and # 2.11 (Krystol T1). The contractor must read those instructions before performing the work.

3.1 Surface Preparation

- A. Concrete surfaces must be clean and free of paint, sealers, form release agents, curing compounds, dirt, laitance or any other contaminates.
- B. Concrete Repair:
 1. Cracks and Joints – Chisel or cut the full length of the crack or joint to provide a rectangular-shaped chase that is 40 mm (1.5 inch) deep x 25 mm (1 inch) wide.
 1. Wall-Slab Joints - Angle the chase so it intersects the joint, removing some concrete from both the wall and the slab.
 2. Tie holes, rock-pockets, honeycombs - Chisel out defective areas to sound concrete. Rout out the defect to a uniform depth. Leave edges square, do not featheredge.
 3. Where reinforcing is encountered, mechanically clean the steel to remove contaminates and rust.
- C. Where concrete will receive Krystol T1 coating or Grout Parge Coat, prepare the surface by high pressure water blasting (minimum 3,000 psi), scarifying, shot blasting or sand blasting to remove loose concrete and surface contaminates.
 1. For Krystol T1 Coating, prepare to ICRI CSP <1-3>.
 2. For paring with Repair Grout, prepare to ICRI CSP <3-5>
- D. Thoroughly rinse all surfaces with water to remove all dust and silt.

3.2 Surface Saturation

- A. All concrete surfaces that receive repair materials must be Saturated Surface-Dry (SSD). The concrete must be completely saturated with water, but all surface water must be removed before installing repair materials. Rewet the surface as needed to maintain SSD conditions during installation.

3.3 Installation – Concrete Repair - Plug Active Leaks

- A. Krystol Plug – Mix to a suitable putty consistency – approximately 4 parts powder to 1 part clean water by volume. Mix only the amount of material that can be installed within one minute.
 1. Install 13 mm (0.5 inches) of Krystol Plug and hold in place until it hardens. Do not overfill.
 2. Install Krystol Plug along the full length/area of the leaking defect until all leakage has stopped.
 3. Wire brush the sides/perimeter of the area to remove excess Plug and rinse with water to expose clean, sound concrete to allow bonding of Krystol Repair Grout.
 4. Ensure a minimum depth of 25 mm remains to install Krystol Repair Grout.

CSI SPECIFICATIONS

03 01 30 CONCRETE MAINTENANCE

3.4 Installation – Concrete Repair – Fill with Grout

- A. Krystol Repair Grout - Mix to a non-sag putty consistency (approximately 4.5 parts of powder to 1-part clean water by volume) using a margin trowel or a drill with a grout mixing paddle.
 1. Firmly install Krystol Repair Grout into the prepared repair area so that it is flush with the surface. Do not leave any voids.
 2. For repairs with minimum width and depth of 50 mm (2 in.) or larger, Krystol Repair Grout may be extended with 10 mm (3/8 in.) pea gravel. Use clean, non-reactive, well-graded gravel complying with ASTM C33. Mix 4 parts grout powder: 2 parts gravel, and up to 1 part water to make a low-slump, cohesive mix. Perform trial batches to confirm workability, as aggregate properties can vary.

3.5 Installation – Resurfacing with Grout Parge Coat:

Note to Specifier: A Parge Coat of Repair Grout is normally only needed for porous surfaces (like concrete block/CMU), or restoring very rough or low concrete cover. If the concrete surface is in acceptable condition, use Krystol T1. When a Grout parge coat is used, Krystol T1 may be applied as the final step.

- A. Krystol Repair Grout
 1. Mix approximately 4 parts powder to 1-part clean water by volume using a margin trowel or a drill with a grout mixing paddle.
 2. Bonding Slurry for Parge Coat – Mix 3 parts powder to 1-part clean water by volume.
- B. Scrub the bonding slurry over the prepared surface to fill voids, then immediately trowel the Parge Coat over the repair area to a thickness of <3 mm (1/8 inch) > <6 mm (1/4 inch) > <specify thickness mm (inch)>

3.6 Installation - Concrete Protection and Waterproofing – Krystol T1:

- A. Krystol T1 – Mix to a thick but spreadable consistency (approximately 3.5 parts powder to 1-part clean water by volume) using a margin trowel or a drill with a grout mixing paddle.
 1. Verify surface is Saturated Surface Dry (SSD).
 2. Brush or spray Krystol T1 evenly over the concrete to achieve a typical coating thickness of 1-1.5 mm <0.04-0.06 inches>. As supplied, the consumption rate of Krystol T1 powder will be <1.2 – 1.6 kg/m² (<2.2 – 3.0 lb/yd²>).
 1. Brush Application - Apply by with a masonry brush using a circular motion to press the coating into low spots. Finish with a lighter pressure to achieve the target coverage and a uniform finish.
 2. Spray Application – Spray evenly over the surface at the specified coverage. Low impact spray equipment will require back brushing to ensure adequate contact between the coating and the concrete. Consult spray equipment manufacturer regarding methods and attachments.

3.7 Protection and Curing

- A. Krystol Repair Grout - Protect fresh grout from rapid drying or freezing for at least 24 hours. Cover with tarps or poly if necessary. Protect the fresh grout from rain until it has fully hardened, and do not apply curing water if the grout has not hardened. Begin wet curing once Krystol Repair Grout has hardened (1-2 hours under most conditions). Wet cure by ensuring the grout remains saturated with water by using hoses and sprinklers, saturated coverings or impermeable coverings. Maintain these curing conditions for at least 72 hours or until Krystol T1 is applied.
- B. Krystol T1 - Protect the freshly applied Krystol coating with tarps or plastic to prevent water loss due to evaporation while it hardens. Leave an air space between freshly applied coating and the protective covering until the coating has set to the touch. Wet curing should begin as soon as the Krystol coating has hardened and will not be damaged by the curing water, usually 6-24 hours depending on temperature. Keep protective coverings in place during the curing period to retain moisture. Apply more curing water if the coating dries out during the curing period. Wet cure for a minimum of 72 hours.

CSI SPECIFICATIONS

03 01 30 CONCRETE MAINTENANCE

3.8 Clean Up

- A. Concrete repair materials - Uncured repair materials can be cleaned from tools with water. Cured repair materials must be removed mechanically.
- B. Leave finished work area in a neat, orderly and clean condition.

3.9 Field Quality Control

Note to Specifier: Only include this section if special field inspection services are required.

- A. Provide free access to Work and cooperate with appointed firm.
- B. Do not conceal installed waterproofing treatment before review by Consultant [and waterproofing manufacturer's representative].
- C. If leaks are discovered, verify with manufacturer whether time period for self-sealing properties of the treated concrete has been exceeded. Make repairs as recommended by the manufacturer and repeat test until no leaks are observed.

3.10 Protection of Finished Work

- A. Protect completed work from damage after application.
- B. Do not backfill for at least thirty six hours (36) after completion of repairs.
- C. If backfilling within 7 days, use damp backfill material.

3.11 Schedules

Note to Specifier: Specify products, location and colour to suite project.

- A. Provide crystalline waterproofing in the following locations

Location	Repair Cracks and Joints	Parge Coat, Resurface	Krystol T1 <Grey><White>
Elevator pits [sump pits, escalator pits]			
Tunnels, underground vaults, dry wells and manholes			
Water tanks, clarifier tanks, digester sections, reservoirs and wet wells			
Planters, fountains, pools			
Retaining walls, sea walls.			
<specify area>			

END OF SECTION

The preceding specifications are provided by Kryton International Inc. as a guide and are not intended to replace sound engineering practice and judgment and should not be relied upon for that purpose. Kryton makes no warranty of any kind, either express or implied, as to the accuracy, completeness or the contents of these guide specifications. Kryton assumes no liability with respect to the provision or use of these guide specifications, nor shall any legal relationship be created by, or arise from, the provision of such specifications. KRYTON SHALL NOT BE RESPONSIBLE UNDER ANY LEGAL THEORY TO ANY THIRD PARTY FOR ANY DIRECT OR CONSEQUENTIAL DAMAGES OF ANY KIND ARISING FROM THE USE OF THESE GUIDE SPECIFICATIONS. The specifier, architect, engineer or design professional or contractor for any particular project bears the sole responsibility for the preparation and approval of the specifications and determining their suitability for a particular project or application. Prior to each use of any Kryton product, the user must always read and follow the warnings and instructions on the product's most current Technical Data Sheet, Application Instruction, product label and Safety Data Sheet which are available online at <http://www.kryton.com> or by contacting an authorized Kryton Representative. Nothing contained in any Kryton document relieves the user of the obligation to read and follow the warnings and instruction for each Kryton product as set forth in the current literature prior to use.